

Oil Jointing (Vegetable Fibre)



SPECIFICATION SHEET

Suitable For: water, aliphatic hydrocarbons, oils and gasoline

Operating Parameters:

Maximum Temp. 100°C

Pressure: 13.8 bar (200 psi)

Material: Vegetable Fibre with glue-glycerine binder

Colour: Brown

Meets specifications:

ASTM-D-170-62T Grade P-3313-B, SAE J90 Grade P-3313-B, MIL-G-12803C Grade P-3313-B and HH-P-96F Type 1

TECHNICAL DATA

ASTM F36	Compressibility %		25 - 40	
ASTM F36	Recovery %		40	
ASTM F152	Tensile – across grain, psi (N/mm ²)		2000 (14)	
ASTM F586	Design Factors	<u>1/16" & under</u>	<u>1/8"</u>	
	"m" factor	9.2	5.5	
	"Y" factor, psi (N/mm ²)	2700 (18.6)	2400 (16.5)	

1404 ARTHUR PORTER DRIVE, BURBUSH, HAMILTON, NZ

PHONE: 0800 238837

EMAIL: SALES@BETTERINDUSTRIAL.CO.NZ WEB: WWW.BETTERINDUSTRIAL.CO.NZ