

Teflex TF150



SPECIFICATION SHEET

Suitable For: water, oils, fuels, alcohols, moderate organic and inorganic acids, and lubricants. Manufactured from inorganic and organic fibres bonded with NBR.

Operating Parameters:

Temperature: Suitable for applications $\leq 150^{\circ}\text{C}$

Pressure: 35 Bar (500 psi)

Material:

Aramid pulp, inorganic & organic fibre bonded with NBR. Asbestos Free.

Colour: Black

This is a good quality general purpose gasket material and is available in the following sizes and thicknesses:

- 4500 x 1500 | 2000 x 1500 mm
- 1500 x 1360 | 3810 x 1270 mm
- 1270 x 1270 | 1500 x 1500 mm

- Thickness: 0.5 - 6.0 mm

TECHNICAL DATA – based on 1.6mm thickness

Density	G/cm ³	1.90±0.1
Tensile Strength ASTM F152	Mpa	≥6.0
Compression Rate ASTM F36	%	7 – 17
Recovery Rate ASTM F36	%	≥30
Leakage Rate ASTM F37	ml/min	≤2.0
Creep Relaxation ASTM F38B	%	≤40

1404 ARTHUR PORTER DRIVE, BURBUSH, HAMILTON, NZ

PHONE: 0800 238837

EMAIL: SALES@BETTERINDUSTRIAL.CO.NZ WEB: WWW.BETTERINDUSTRIAL.CO.NZ